



ISR 70-05 AP sskf

ADVANCED PERFORMANCE

The Simson Industrial Special Range is a range of high tech quality products especially developed for industrial applications.

Product

Simson ISR 70-05 AP sskf is a Silyl Modified Polymer (SMP) based adhesive with a high tensile strength and is suitable for making elastic constructive joints but can also be used as a sealant. ISR 70-05 AP sskf has been tested and certified to the International Maritime Organisation Fire Test Procedures for Surface Flammability, resolution A.687 and is approved for bonding deck materials onto steel or aluminium. ISR 70-05 AP sskf used with the Dual SMP[®] technology guarantees an increased and controlled cure speed and reliability in the production process and extends the application possibilities.

Applications

- Elastic bondings and sealings in e.g. bus-, caravan-, train- and yacht construction.
- Bonding of roofs on busses, trains, trucks.
- Bonding of corner profiles of aluminium or polyester on trailers.
- Bonding of polyester parts on metal frames.
- Bonding of floor systems.

Features

- Solvent-, isocyanate- and PVC free.
- Very good UV-resistance and ageing properties.
- In general good adhesion on several substrates without the use of a primer.
- Permanently elastic in a temperature range of -40°C to +120°C.
- Neutral, odourless and fast curing.
- Paint compatible with most industrial paint- or lacquer systems, both alkyd resin and dispersion based (due to the large scale of different types of industrial paints a paint compatibility test is recommended).
- Paintable after skin forming (wet on wet); this will not significantly influence the curing speed.

Adhesion


In general ISR 70-05 AP sskf adheres well without primer on clean, dry, dust- and grease free substrates of aluminium, stainless steel, galvanised steel, zinc, copper, brass, powder coated metal, most lacquered metal surfaces, glass, PVC, polyester (GRP), painted and lacquered wood, etc. No adhesion on untreated polyethylene, polypropylene and teflon. In those cases where, due to great thermal or physical loads and especially under wet conditions, high adhesion demands are needed, the use of Simson Prep M is recommended. Prep M degreases and prepares the surface of the substrate in one step. On plain, untreated wooden surfaces and other porous substrates Simson Prep P is recommended. For more details concerning Prep M and Prep P consult the specific Technical Data Sheets. For not mentioned substrates and additional information consult Bostik.

Method of use

ISR 70-05 AP sskf can easily be extruded with a hand- or air pressure gun at temperatures between +5°C and +35°C. In sealing applications ISR 70-05 AP sskf should be tooled or smoothed within 20 minutes (at 20°C/50% R.H.) with a spatula or putty knife, occasionally moistened with a soap solution. Avoid soap solution penetrating between joint sides and sealant, because this will create loss of adhesion.

Please refer to the disclaimer and contact information at the bottom of the final page of this Technical Data Sheet.

Page 1 of 2

**Bostik**

The Adhesive Company



ISR 70-05 AP sskf

In bonding applications the substrates have to be assembled within 30 minutes (at 20°C/50% R.H.) after applying ISR 70-05 AP sskf. In general an adhesive thickness of 2 mm is recommended. At a temperature of +20°C and a relative humidity of 50% ISR 70-05 AP sskf can be painted with the most industrial paints already 10 minutes after application. Best adhesion of paint coats is generally obtained if painted within 4 hours after applying ISR 70-05 AP sskf. Cleaning tools or removing uncured residue of ISR 70-05 AP sskf can be done with a clean colourless cloth, wetted with Simson Liquid 1. It is recommended to make a trial first to check possible attack of the substrate by Liquid 1.

Technical data

Basic material	Silyl Modified Polymer (SMP)	
Curing method	moisture	
Specific gravity	ca. 1.5 g/ml	
Skin forming time	ca. 20 min.	(20°C/50% R.H.)
Open time	< 30 min.	(20°C/50% R.H.)
Curing speed after 24 hrs	ca. 3 mm	(20°C/50% R.H.)
Shore A hardness	ca. 60	(DIN 53505)
Volume change	< 3%	(DIN 52451)
Tensile stress (100%)	ca. 2.3 MPa	(DIN 53504/ISO 37)
Tensile stress at break	ca. 2.9 MPa	(DIN 53504/ISO 37)
Elongation at break	ca. 250%	(DIN 53504/ISO 37)
Shear stress	ca. 2.4 MPa	(DIN 53283/ASTM D1002)
	<small>(Alu-Alu; adh. thickness 2 mm, test speed 50 mm/min.)</small>	
Tear propagation	ca. 16 N/mm	(DIN 53515/ISO 34)
	<small>(Type C, test speed 500 mm/min.)</small>	
E-Modulus(10%)	ca. 5.5 MPa	(DIN 53504/ISO 37)
Solvent percentage	0%	
Isocyanate percentage	0%	
Temperature resistance	-40°C till +120°C	
Application temperature	+5°C till +35°C	
UV- and weather resistance	excellent	
Colours (standard)	white, black, grey	
Packaging	290 ml cartridges, 400 ml and 600 ml sausages, other packaging on request	

Storage stability

ISR 70-05 AP sskf can be stored for 12 months in an original, unopened container in a dry place at temperatures between +5°C and +30°C (cartridges 18 months).

Further information

The following publications are available on request:

- Material Safety Data Sheets (MSDS)

UK

Bostik Ltd.
Stafford
Tel: +44 (0) 1785 27 27 27
Fax: +44 (0) 1785 22 26 65

France

Bostik S.A.
Paris
Tel: +33 (0) 1 74 96 91 18
Fax: +33 (0) 1 47 96 94 20

Germany

Bostik GmbH
Borgholzhausen
Tel: +49 (0) 54 25/8 01-0
Fax: +49 (0) 54 25/80 11 40

The Netherlands

Bostik B.V.
's-Hertogenbosch
Tel: +31 (0) 73 6 244 244
Fax: +31 (0) 73 6 244 344

For more Bostik locations please consult www.bostik.com

Bostik
The Adhesive Company

All figures, recommendations and safety precautions are based on thorough investigations and our actual experience and are without engagement. Although the documentation has been set up with most carefulness, we do not accept any responsibility for mistakes, inaccuracies or printer's errors. We reserve the right to adjust the product, whenever we feel necessary. Because the design, the quality of the substrate and the conditions during application fall beyond our control, no responsibility for executed works can be accepted on the basis of this documentation. We therefore recommend to carry out own tests on the spot. All our sales and deliveries are subject to our general sales- and delivery conditions.